



1. Identification of the substance /preparation and of the company / undertaking

CLEAR RESIN AND CASTING RESIN: GC 206 BLUE 5900, GC207 BLUE 5900

Company

NORD COMPOSITES

ZA route d'Amiens

80890 CONDE FOLIE – France

Tel : 03.22.31.57.57

Fax : 03.22.31.86.97

2. Composition / information on ingredients

Chemical description

Unsaturated polyester, melted in styrene

For resin RM 680, vinylester dilute in styren

Hazardous components

Styrene (CAS number :100-42-5) 40%

Solid polyester 55%

Pigment paste 5%

3. Hazards identification

Hazard for men and environment

R10 – flammable

R20 – noxious by inhalation

R36/38 – eye and skin irritant

4. First aids measures

- Inhalation Move to fresh air, keep the affected person warm and at rest.
- Skin contact Take off immediately all contaminated clothing, wash off with soap and plenty of water
- Eye contact rinse immediately with plenty of water for at least 10 minutes, and seek medical advice.
- Ingestion Do not induce vomiting, get medical attention

5. Fire fighting measures

Extinguishing media : foam, powder, carbon dioxid, water spray can be used

Specific hazards : toxic gases / vapours / fumes of carbon dioxide, carbon monoxide, water.

Special protective equipment for fire fighters : Wear a self-contained breathing apparatus

6. Accidental release measure

Personal precautions : In case of vapour formation use respirator

Environmental precautions : Do not let product enter drains

Methods for cleaning up : Soak up with inert absorbent material (for example : sand, silica gel, universal blinder). Clean contaminated surface thoroughly and place into containers.

7. Handling and storage

Handling

Keep away from sources of ignition, no smoking.

Storage

Keep container tightly closed in a dry and well-ventilated place, keep away from heat.



8. Exposure controls / personal protection

Substance

Styrene : VME = 50 ppm (215 mg/m³)

Personal protection equipment :

- respiratory protection : In case of insufficient ventilation wear suitable respiratory equipment.
- hand protection: solvent-resistant gloves.
- eye protection: safety glasses
- skin protection : long sleeved clothing

9. Physical and chemical properties

Form :	Liquid
Odour :	Typical
Boiling point :	146°C
Flash point :	31°C
Ignition temperature :	490°C
Explosion limits :	
- Lower	1.1%
- Upper	8.0%
Vapour pressure :	20°C
Density :	approximately 1.15 – 1.3 g/cm ³
Solubility:	insoluble in water, soluble in styrene, xylene acetone
PH :	no suitable
Viscosity :	>300 mPa.s

10. Stability and reactivity

Stability may polymerise

Hazardous decomposition products : no decomposition in normal conditions, heat emanation during polymerisation

11. Toxicological information

Acute toxicity

Styrene – DL50/ oral / rat : 5000 mg/kg
CL50/ inhal / rat : 11.9mg/l/4h

12. Ecological information

Test : OCDE 301C/ ISO 9408 / EEC 84/449/V,C7
Analysis : DBO
Elimination rate : > 60 %
Estimate : biodegradable
Insoluble, do not discharge in natural waters.

13. Disposal considerations



No hard : Can be incinerated in properly designed furnace complying with local regulations

Hard : Can be placed in dump or incinerated in properly designed Empty containers that cannot be cleaned must be destroyed as well as the product they contain.

14. Transport information

Road : ADR/RID/GGVS/GGVE Class : 3

Pictogram

Hazards N° : 30

UN : 1866

Sea : IMDG/GGVSee_ Class : 3

UN : 1866

Packaging group : III

EMS N° : 3-05

MFAF N° 310

Marine pollutant : yes

Air : OACI/IATA

Class : 3

UN : 1866

Packaging group : III

Proper shipping name : resin solution, flammable (contains styrene) – marine pollutant

15. Regulatory information

Classification according to EEC directive

Contains : styrene

EEC N° : 601-026-00-0

EINECS N° 202-851-5

Xn – noxious

R10 flammable

R20 noxious by inhalation

R36/38 eye and skin irritant

S3 Keep in a cool place

S37 wear appropriate gloves

S51 only use in ventilated areas

16. Other information

Realisation of composite material

For more details, refer to the Data sheet.

This safety data sheet relates information based on our present state knowledge. It does not constitute a guarantee for product characteristics. It is the user's responsibility himself as to the suitability of such information for his own particular use.